

R574 Flame Rated Sheet



Spartech R574 is RoHS compliant, non PVC & PBDE containing, flame retardant ABS engineered to meet the flammability requirements for today's most demanding applications. R574 is UL listed in all colors, 94-VO @ 0.063 and UL94 5VA @ 0.125.

TYPICAL PROPERTIES

TEST	CONDITION	UNITS	VALUE
Specific Gravity	D-792		1.20-1.27
Izod Impact	D-256	(ft-lbs./in.)	4.5
Tensile Strength	D-638	(psi)	5,200
Flexural Strength	D-790	(psi)	8,000
Flexural Modulus	D-790	(psi)	320,000
Heat Deflection Temp			
264 psi	D-648	Deg F	190
Hardness	D-648	Rockwell R	98
Flammability	UL94 V-0		Listed .063
	UL94 5VA		Listed .125
	MVSS 302		Passes

Disclaimer: The values shown above are representative of values that have been obtained in the testing of sheet samples produced in various colors. Each user of the material should conduct his own testing and evaluations to determine the effectiveness, safety, and suitability of the material for its particular use, specifically to include testing of prototype parts in their intended end use.

Contact Information

Spartech Plastics, Royalite Specialty Sheet, (574) 267-7127, 3454 N. Detroit Street, P.O. Box 958, Warsaw, IN 46581-0958

For additional information, please contact Spartech Corporation at (888) 721-4242 or visit our web site at www.spartech.com.

Page 1 of 1

Use and conditions and applicable laws may differ from jurisdiction to jurisdiction, and may be subject to change at any time. Customers are responsible for determining whether products and information are appropriate for their use. Spartech Corporation and its subsidiaries assume no liability for the accuracy or completeness of information contained herein, and all information is subject to change without notice. No freedom from infringement of any patent, trademark or copyright owned by Spartech or any of its subsidiaries is to be inferred. NO WARRANTIES, EXPRESS OR IMPLIED, ARE GIVEN; ALL IMPLIED WARRENTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

