



***Spartech PEP***  
**Korad® & Specialty Products**

Technical Data		Korad Klear		05702 at .003"	
Property	Unit	Typical Values	Test Method		
Gravity		1,15	ASTM D-792		
Area Yield	square feet / lb.	55,7	Internal		
Tensile Strength	psi	3.400	ASTM D-882		
Tensile Elongation	% minimum	20,0	ASTM D-882		
Tensile Stress at Yield	psi	3.800	ASTM D-882		
Tear Resistance (Elmendorf)	gms minimum	16	ASTM D-1922		
Gloss (60)	% maximum	12,0	ASTM D-523		
Light Transmission	% minimum	88,0	ASTM D-1003		
Haze	% maximum	NA	ASTM D-1003		
UV Transmission	% maximum	0.0 @ 320 nanometers 0.0 @ 350 nanometers 0.0 @ 360 nanometers 1.5 @ 370 nanometers	Internal		

Korad is a trademark of Spartech PEP.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine suitability of our materials and suggestions before adopting them on a commercial scale.

Spartech PEP Product Development personnel are available to furnish technical assistance for users' evaluations of the suitability of intended uses or applications of Korad acrylic film. Users' evaluations should include any testing or analysis deemed necessary or appropriate. No statement, illustration or information contained in this brochure shall constitute either an express or implied warranty. There is no implied warranty of merchantability of fitness for a particular purpose of Korad acrylic film.